



RILEY EQUIPMENT COMPANY

Riley Equipment Company
 6911 Gant Road
 Houston, Texas 77066
 recogroup@sbcglobal.net
 (281) 583-5295 Fax: (281) 583-5299

Virgin Granular Activated Coconut Carbon

Our line of Virgin Granular Activated Coconut Carbon in 4x8 mesh (VGACC-4x8) is made from coconut shells and activated through high temperature & high pressure steam in order to create the internal pore structures which offer maximum efficiency in the adsorption process. It is desirable to have the greatest possible surface area within the smallest possible volume and Granular Activated Carbon brings that to the table with over 1,210,000 meters of surface area per gram.

APPLICATION: For vapor filtration. Superior adsorption of hydrocarbons, halogenated hydrocarbons, benzene, aromatics, acetone, ethanol, freons, solvents and mercaptans.

CARBON PROPERTIES:

Total Surface Area, minimum (Bet Method)	1100-1150 m ² /gm
Bulk Density (lbs./Ft ³)	<30
Apparent Density, minimum (ASTM 2864)	0.45-0.55 gm/cc
Particle Size Distribution	4x8 U.S. Mesh
Larger than #4 mesh, maximum	5%
Smaller than #8 mesh, maximum	5%
Mean Particle Diameter	3.7 mm
Hardness, minimum (ASTM 3802)	98
Iodine Number, minimum (ASTM 04607)	1150 mg/gm
CCL ₄ Activity, minimum (ASTM 03467)	60%
Moisture Content, maximum (ASTM 02867)	5%
Ash Content, maximum (ASTM 2866)	10%

Standard Packaging: <30 lb. boxes. 220 lb. drums. 1100 lb. super sacks available.

Safety Notice: Wet Activated Carbon depletes Oxygen and creates a severe safety hazard for people working in confined spaces such as inside filters.

All information presented herein is believed reliable and in accordance with accepted engineering practices. Riley Equipment makes no warranties as to the completeness of this information. Users are responsible for evaluating individual product stability for specific applications. Riley Equipment assumes no liability whatsoever for any special, indirect or consequential damages arising from the sale, resale, or misuse of its products.